

# KA183-85


Low Temperature HNBR for Energy,  
Oil & Gas Applications



## Low temperature HNBR:

Parker Hannifin is recognized worldwide for leadership in elastomer development. One creation is KA183-85, a low temperature hydrogenated nitrile (HNBR) material designed for energy, oil and gas applications. It has excellent cold temperature attributes, formulated to withstand temperatures as low as -58°F (-50°C).

In subsea oil exploration and production of crude oil and natural gas, application temperatures can reach close to freezing point. Most seal materials are slow to rebound from these harsh temperatures which limit their sealing capacity.



## Contact Information:

Parker Hannifin Corporation  
**O-Ring Division**  
2360 Palumbo Dr.  
Lexington, KY 40509

phone 859 269 2351  
fax 859 335 5128

[www.parkerorings.com](http://www.parkerorings.com)

## Recommended For Use In:

- NORSOK sour gas approved
- Temperature capability as low as -58°F (-50°C)
- 300°F (149°C) performance rating
- Passed NACE TM0192-2003
- Passed NACE TM0297-97
- Good extrusion resistance



ENGINEERING YOUR SUCCESS.

KA183-85 Material Test Report		
Original physical properties	Test method	Test results
Hardness, shore A, pts.	ASTM D2240	86
Tensile strength, psi	ASTM D412	3023
Elongation, %, min.	ASTM D412	135
Modulus @ 100% elongation, psi	ASTM D412	2117
Specific gravity	ASTM D297	1.36
Compression Set 70 hrs. @ 302°F		
Percent of original deflection	ASTM D395 Method B	20
Dry Heat Resistance 70 hrs. @ 302°F		
Hardness change, pts.	ASTM D573	+7
Tensile strength change, %		-5
Elongation change, %		-22
Distilled Water, 70 hrs. @ 212°F		
Hardness change, pts.	ASTM D471	+4
Tensile strength change, %		-9
Ultimate elongation change, %		-9
Volume change, %		+4
Diesel #2 Low Sulfur, 70 hrs. @ 212°F		
Hardness change, pts.	ASTM D471	-18
Tensile strength change, %		-28
Ultimate elongation change, %		-31
Volume change, %		+30
Methanol, 70 hrs @ RT		
Hardness change, pts.	ASTM D471	-6
Tensile strength change, %		-35
Ultimate elongation change, %		-23
Volume change, %		+8
Erifon 818, 70 hrs. @ 158%		
Hardness change, pts.	ASTM D471	+3
Tensile strength change, %		-3
Ultimate elongation change, %		-15
Volume change, %		0
Baroid ZnBr, 70 hrs. @ 212°F		
Hardness change, pts.	ASTM D471	+13
Tensile strength change, %		+55
Ultimate elongation change, %		-33
Volume change, %		+15
Low temperature		
TR-10, °C	ASTM D1329	-39
Explosive Decompression		
Per NACE standard TM0192-2003	Rating	1-No damage

KA183-85 excels in low temperatures, remaining flexible and allowing the sealing properties to remain robust.

Another benefit of this 85 durometer material is its excellent tensile, modulus, and elongation properties. As an HNBR, KA183-85 is compatible with hydrogen sulfide, corrosion inhibitors, steam, methanol and oil.

KA183-85 has passed extensive testing in high pressure CO2 and decompression per NACE standard TM0297-97 with outstanding results.

